

#### PRODUCT DESCRIPTION

A paint stripper especially formulated for removal of antifoulings. Interstrip AF is not aggressive and will not damage gelcoats.

#### PRODUCT INFORMATION

|                    |               |
|--------------------|---------------|
| Colour             | YMA171        |
| Specific Gravity   | 0.9           |
| Volume Solids      | 6.20%         |
| Typical Shelf Life | 2 yrs         |
| VOC (As Supplied)  | 774 g/lit     |
| Unit Size          | 750 ml 2.5 Lt |

#### DRYING/OVERCOATING INFORMATION

##### Drying

##### Overcoating Substrate Temperature

|               | 5°C (41°F) |     | 10°C (50°F) |     | 23°C (73°F) |     | 35°C (95°F) |     |
|---------------|------------|-----|-------------|-----|-------------|-----|-------------|-----|
| Overcoated By | Min        | Max | Min         | Max | Min         | Max | Min         | Max |

#### APPLICATION AND USE

|                                 |   |
|---------------------------------|---|
| <b>Preparation</b>              | Wash off loose antifouling with fresh water, preferably at high pressure. Mask off areas to be stripped.  |
| <b>Method</b>                   | Apply liberally with an old broad brush (75-150 mm) using a stippling action to get a good thickness. Work systematically around the hull covering approximately 1-2 m at a time, ensuring adequate ventilation. Leave on the surface for at least 10 minutes. Remove while still soft with a blunt wooden scraper. Heavy build up may require more than one application. |
| <b>Hints</b>                    | <b>Cleaner</b> Clean up, when still wet, with water. Once paint has dried: YTA085 Thinners No.3<br><b>Other</b> Ensure adequate ventilation during use.   |
| <b>Some Important Points</b>    | No special restrictions.  |
| <b>Compatibility/Substrates</b> | Suitable for use on GRP, Steel, Aluminium and Wood.   |
| <b>Number of Coats</b>          | Variable  |
| <b>Coverage</b>                 | (Theoretical) - 0 m <sup>2</sup> /lt Variable.  |
| <b>Application Methods</b>      | Brush   |


#### TRANSPORTATION, STORAGE AND SAFETY INFORMATION

|                |   |
|----------------|---|
| <b>Storage</b> | <b>GENERAL INFORMATION:</b><br>Exposure to air and extremes of temperature should be avoided. For the full shelf life of Interstrip AF to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.<br><b>TRANSPORTATION:</b><br>Interstrip AF should be kept in securely closed containers during transport and storage.  |
| <b>Safety</b>  | <b>GENERAL:</b> Read the label safety section for Health and Safety Information, also available from our Technical Help Line.<br><br><b>DISPOSAL:</b> Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.<br>Remainders of Interstrip AF cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities. |


#### IMPORTANT NOTES

*The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal*

Please refer to your local representative or visit [www.yachtpaint.com](http://www.yachtpaint.com) for further information.

, International®, the AkzoNobel logo and other products mentioned in this publication are trademarks of, or licensed to Akzo Nobel. ©Akzo Nobel 2009.

Ref:3225 Issue Date:21/07/2010



Interstrip AF  
Special Products  
One-Pack Paint Stripper




---

*or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.*

---

Please refer to your local representative or visit [www.yachtpaint.com](http://www.yachtpaint.com) for further information.

 International®, the AkzoNobel logo and other products mentioned in this publication are trademarks of, or licensed to Akzo Nobel. ©Akzo Nobel 2009.

Ref:3225 Issue Date:21/07/2010