Precision
YACHT PAINT

TECHNICAL DATA SHEET

TDS: PMG139

PRECISION ANTI-SLIP DECK PAINT

PM/G139/ ALL

DESCRIPTION:

Precision Anti-slip Deck Paint contains a pre-mixed coarse aggregate to maximise grip in the harshest conditions. Designed to be very hard wearing, decorative and provides a good degree of protection.

RECOMMENDED USE:

Precision Anti-slip Deck Paint is a ready prepared paint. Can be applied to concrete, GRP, and suitably prepared wood and metal.

AVAILABILITY:

1 litre, 2.5 litre

FINISH:

Aggregated

COLOUR:

White, Grey, Blue, Cream and Light Grey

TYPICAL S.G. (SPECIFIC GRAVITY):

1.35 - 1.55 @ 20 °C

VOLUME SOLIDS:

60%

WET FILM THICKNESS W.F.T

100 - 150 microns

DRY FILM THICKNESS D.F.T

60 - 100 microns

EXPECTED SPREADING RATE:

6 - 10 sq.m / litre

60 - 100 micron d.f.t (based on brush application)

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

6.5 Poise @ 25 °C

FLASH POINT:

Above 32 °C (closed cup)

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry:	6	hours @ 20 °C
Hard dry:	24	hours @ 20 °C
Full hardness:	5 - 7	days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

Minimum 16 hours / Overnight dry

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

343 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application restrictions	N/A	
Method:	Brush or	Short/medium roller
Thinner (Max vol):	Do not thin	
Nozzle size:		
Nozzle pressure:	N/A	
Cleaning solvent:	General Purpose	

For further advice contact Precision Yacht Paint Technical Services on +44 (0)1482 381456

The physical constants are subject to normal manufacturing tolerances.

Precision Yacht Paint
Lockwood Street, Hull, East Yorkshire, HU2 0HN
Tel.: +44 (0)1482 381456

Recoat interval:	Minimum 16 hours / Overnight dry

SURFACE PREPARATION:

All surfaces should be clean, dry, sound and free from contaminants. Surfaces have to be prepared and primed with the suitable primer for that substrate. Existing painted surfaces - Surfaces should be cleaned, degreased and sanded to ensure an adequate "key" is produced. Remove all loose and flaking material and treat bare areas as new substrate and prepare accordingly.

MIXING INSTRUCTIONS:

Stir well before use. DO NOT USE MECHANICAL SHAKER!

APPLICATION CONDITIONS:

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

Precision Wood Primer (Aluminium) on wood, Precision Anti-corrosive Metal Primer on ferrous metals, apply direct to GRP decks.

SUBSEQUENT COAT:

Precision Anti-slip Deck Paint

REMARKS:

HEALTH AND SAFETY:

See safety data sheet - SDS 11595

ISSUED:

22 November 2016

REVISION:

1

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specificaton. In case of doubt as to the suitability of the product please contact our Technical Service Department on +44 (0)1482 381456.

For further advice contact Precision Yacht Paint Technical Services on +44 (0)1482 381456

The physical constants are subject to normal manufacturing tolerances.

Precision Yacht Paint
Lockwood Street, Hull, East Yorkshire, HU2 0HN
Tel.: +44 (0)1482 381456